



# Selectarc 316HR

High efficiency  
Stainless Electrode

## Classification

AWS A5.4 : E316L-26      EN 1600 : E 19 12 3 L R 7 3  
ISO 3581-A : E 19 12 3 L R 7 3

## Description & Applications

Synthetic electrode with high recovery (160%) and a Rutile-basic coating giving a 316 L deposit with approx. 8% delta ferrite. Easy striking, soft arc, slag lifts by itself, clean spatter-free welds, finely rippled beads. Used for high efficiency welds, fast deposition, long beads. To weld stainless steels of similar composition in : pulp and paper industry, foodstuff industry...

## Base materials

### Stainless steels for general use:

UNS	Alloy	EN 10088	Mat. N°	UGINE
S31600	316	X5CRNiMo17-12-2	1.4401	UGINOX 17-10 M
S31603	316L	X2CrNiMo17-12-2	1.4404	UGINOX 18-11 ML
J92900		G-X5CrNiMo19-11-2	1.4408	
S31635	316Ti	X6CrNiMoTi17-12-2	1.4571	UGINOX 17-11 MT
S31635	316Ti	X10CrNiMoTi18-12	1.4573	
S31640	316Cb	X6NiCrMoNb17-12-2	1.4580	
		G-X5CrNiMoNb19-11-2	1.4581	

## Typical Weld Metal Composition ( % )

C	Si	Mn	Cr	Ni	Mo	Fe
<0.04	0.9	0.7	18.0	11.5	2.5	Rem.

## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
>380	>560	>30	+20°C >60

## Welding Current & Instructions

Electrode	ØxL ( mm )	1,6x250	2,0x350	2,5x350	3,2x350	4,0x450
Current	( A )	50	60	90	120	150

Redrying at 300°C during 1h, if necessary. Interpass temperature : < 150°C.

ind.12



= + ~ 55V

**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.