



Selectarc 316VD

*Stainless Steel Electrode
For vertical down*

Classification

AWS A5.4 : E316L-16

EN 1600 : E 19 12 3 L R 3 1

ISO 3581-A : E 19 12 3 L R 3 1

Description & Applications

Low carbon Rutile-basic coated electrode, giving a Mo-containing austenitic stainless steel deposit. This electrode is designed for vertical down welding on Cr-Ni-Mo stainless steels and clad steels which are applied at service temperatures from -120°C up to +400°C in the chemical and petrochemical industries, in refineries...

Base materials

Stainless steels for general use:

UNS	Alloy	EN 10088	Mat. N°	UGINE
S31600	316	X5CrNiMo17-12-2	1.4401	UGINOX 17-10 M
S31603	316L	X2CrNiMo17-12-2	1.4404	UGINOX 18-11 ML
J92900		G-X5CrNiMo 19-11-2	1.4408	
S31635	316Ti	X6CrNiMoTi17-12-2	1.4571	UGINOX 17-11 MT
S31635	316Ti	X10CrNiMoTi18-12	1.4573	
S31640	316Cb	X6NiCrMoNb17-12-2	1.4580	
		G-X5CrNiMoNb19-11-2	1.4581	

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Mo	Fe
<0.03	0.8	0.7	18.0	11.5	2.5	Rem.

All Weld Metal Mechanical Properties


R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>400	>560	>30	+20°C >60

Welding Current & Instructions

Electrode	ØxL (mm)	2,0x300	2,5x300	3,2x350
Current	(A)	50	70	100

Redrying at 250°C during 1h. Interpass temperature : < 150°C.

ind.12



= + ~ 80V



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.