



# Selectarc B-Fonte

Cast Iron Rod  
For hot Welding

## Classification

DIN 8573 : G FeC-1

ISO 1071 : R C FeC-1

## Description & Applications

Welding rod for oxy- acetylene hot welding of grey cast iron. The deposit shows the same colour and structure as grey cast iron.

Mainly used to weld defects in foundries.

### Base materials

Cast iron:

ASTM	DIN	NFA
A48 Class 25B – Class 60B	GG-15 to GG-40	FGL 150 to FGL 400

## Typical Composition (%)

C	Si	Mn	Ni	Cu	Fe
3.3	3.2	0.5	0.5	0.1	Rem.

## All Weld Metal Mechanical Properties

Hardness  
~185 HB  
After PWHT

## Welding Current & Instructions

Electrode	ØxL ( mm )	4,0x450	5,0x450	6,0x450	8,0x450	10,0x450
-----------	------------	---------	---------	---------	---------	----------

Prepare the casting defect to be repaired, preheat the piece to 550-650°C, keep this temperature during welding, cool slowly down preferable in a furnace. Use a neutral flame and a corresponding flux.

ind.12



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.