



# Selectarc B63

*Basic coated Electrode  
For creep resisting steels*

## Classification

AWS A5.5 : E8018-B2                      EN 1599 : E CrMo1 B 4 2 H5  
ISO 3580-A : E CrMo1 B 4 2 H5

## Description & Applications

Low hydrogen basic coated electrode alloyed with Cr and Mo for welding creep resisting steels with 1% Cr - 0.5% Mo. Resistant to high temperature up to 500-550°C. For piping systems, boilers, overheaters. Soft fusion, good slag removal. Nice aspect of the weld bead.

**Main applications:** Petrochemistry, chemical industry.

### Base materials :

### Tube & steels for boiler and pressure vessels :

EN	: 15Cr3 – 16 MnCr 5 – 20 MnCr 5 – 24 CrMo 5 – 15 CrMo 5 13 CrMo 4 4 - 22 CrMo 4 4 – GS 17 CrMo 5 5
Material N°	: 1.7015 – 1.7131 – 1.7147 – 1.7223 – 1.7225 – 1.7258 1.7262 – 1.7335 – 1.7337 – 1.7350 – 1.7357
ASTM	: A335 Gr.P12 – A387 Gr.12Cl2 – A193 Gr B7 – A182 Gr F11 A336 Gr F12 – A217 Gr WC6

## Typical Weld Metal Composition ( % )

C	Si	Mn	Cr	Mo	P	S	Fe
<0.12	0.4	0.8	1.1	0.5	<0.025	<0.025	Rem.

## All Weld Metal Mechanical Properties \*

R <sub>e</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
>460	>550	>19	+20°C >120


\* After heat treatment at 700°C/1h

## Welding Current & Instructions

Electrode	ØxL ( mm )	2,5x350	3,2x350	4,0x450	5,0x450
Current	( A )	80	115	150	190

Redrying: 1h at 350°C, if necessary. Preheating of joints to weld: 200-250°C. Interpass temperature: 150-250°C. Annealing after welding is advised at 700°C/1-2h.

Ind.12



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.