



Selectarc B691NM

*Basic coated Electrode
For creep resisting steels*

Classification

AWS A5.5 : E9015-B9 EN 1599 : E CrMo91 B 4 2 H5
AWS A5.5M : E6215-B9 ISO 3580-A : E CrMo91 B 4 2 H5

Description & Applications

Low hydrogen basic coated electrode for welding creep resistant steels of similar chemical composition (known as P91) used at service temperatures up to 650°C. Especially designed for welding castings which require Mn+Ni<1.0%. The deposit is resisting to temperature and creep up to 650°C and highly resistant to hot gas and overheated steam.

Main applications: For power plants, heat exchangers, tubes, steam boilers,...

Base materials

Plates and pipes for boiler and pressure vessels

Mat. N°	EN	UNS	ASTM
1.7386	X12CrMo9-1	K91560	A187 Gr F9 ; A336 Gr F9; A335 Gr P9
1.7389	GX12CrMo10-1	J84090	A217 C12
1.4903	X10CrMoVNb9-1		A199 gr. T91 ; A335 gr. P91 ; A213 gr T91

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Mo	Cu	V	Nb	N	P	S	Mn+Ni
0.09	0.25	0.45	8.9	0.45	1.0	0.04	0.2	0.05	0.04	0.01	0.008	<1,0

All Weld Metal Mechanical Properties *

$R_{p0,2}$ (MPa)	R_m (MPa)	A_5 (%)	KV (J)
620	730	18	+20°C 60



* After heat treatment at 760°C/2h

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x450
Current	(A)	80	115	150

Redrying: 1h at 300°C, if necessary. Preheating of joints to weld at 200°C. Interpass temperature: 200-300°C. Slow air cooling to a temperature below 80°C followed by an annealing at 760°C / 2-6h, then slow cooling. To achieve improved impact resistance, thin layers with about 2mm thickness should be welded.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr