



# Selectarc B842

*Basic Electrode  
For cold tough steels*

## Classification

AWS A5.5 : E7018-G      EN 499 : E 42 6 1Ni B 4 2 H5  
ISO 2560-A : E 42 6 1Ni B 4 2 H5

## Description & Applications

Low hydrogen basic coated electrode alloyed with Nickel for welding steels with high strength and high toughness, resistant to low temperature down to -60°C. Used for weld joints exposed to low temperature. Regular fusion, nice aspect of the deposit.

### Base materials

#### Fine grain construction steels, cold tough:

EN :	S185 – S355 – P235GH – P355 – L210 – L415 – S/P275 – S/P460 - E295 – E335 – E360 – P295GH – P355GH – P235 – P265 – A St35 – A St52 – GP240R.
ASTM :	A302 Gr A, B, C, D – A333 Gr 126 – A414 Gr G – A487 Gr BQ CQ A521 Gr AA, AB, CE, CF, LF1 – A537 C12 – A572 Gr 60&65 A350 Gr 126 – A350 Gr LF1, LF2 – A607 Gr 60&65 – A633 Gr A&B LF5 A668 Gr E&F – A714 Gr I à VI

## Typical Weld Metal Composition ( % )

C	Si	Mn	Ni	P	S	Fe
0.06	0.4	1.2	0.9	<0.025	<0.020	Rem.

## All Weld Metal Mechanical Properties


R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
>470	550-680	>22	-60°C 50

## Welding Current & Instructions

Electrode	ØxL ( mm )	2,5x350	3,2x350	4,0x450	5,0x450
Current	( A )	80	115	150	190

Redrying at 300°C during 2h, if necessary. Eventual preheating of the weld joint at 100°C. Interpass temperature: <250°C. A thermal stress relieving heat treatment is advised at 550°C during 1-2 hours.

Ind.12



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.