



Selectarc Co25

Cobalt base Hardfacing
Electrode "Grade25" type

Description & Applications

Surfacing electrode with a rutile-basic coating. Cobalt base deposit of « grade 25 » type (Co-Cr-W-Ni). Deposit characterised by a good resistance to metal-metal wear and oxidation resistant up to 1000°C. Good behaviour to important thermal and mechanical shocks. Excellent resistance to cracks, highly resistant to cavitation and erosion, deposit non-magnetic.

General applications : Surfacing of motor valves, gas turbine blades, extrusion nozzles, forging dies, forging tools.

All Weld Metal Mechanical Properties

Hardness (as welded) +20°C
~ 230 HB

Hardness at +600°C
~300 HB

Welding Current & Instructions

Electrode	ØxL (mm)	3,2x350	4,0x350
Current	(A)	100	140

Redrying 1h at 250°C, if necessary. Preheat massive pieces 250-400°C. Keep this temperature during welding, cool down slowly after welding to reduce the risk of cracking while cooling.

ind.13



= + ~ 70V



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.