



Selectarc Cu110

Copper Electrode

Classification

AWS A5.6 : ~E Cu DIN 1733 : EL-CuMn2
 UNS : ~W60189 Material N° : 2.1363

Description & Applications

Basic coated electrode for welding different pure copper grades and copper-nickel alloys in some cases too. Also used for dissimilar joints and surfacing. The deposit is free of porosity and gives a tensile strength similar to that of most commercial copper types.

Main applications: Joining of electrical copper electrodes used in furnaces, for joining copper to steel bars in electrically heated drive ways.

Base materials

UNS	DIN	Material N°
C10100	OF-Cu	2.0040
C11000	E-Cu	2.0060
C10300	SE-Cu	2.0070
	SW-Cu	2.0076
C11020	F-Cu	2.0080
C12200	SF-Cu	2.0090

Typical Weld Metal Composition (%)

Mn	Sn	Fe	Cu
1.5	0.8	0.1	Rem.

All Weld Metal Mechanical Properties


R _m (MPa)	A ₅ (%)	Hardness	Electrical conductivity
~200	35	~60 HB	15-20 S*m/mm ²

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x350
Current	(A)	70-90	90-120	110-140

Redrying 2 h at 150 °C. Joints to weld must be clean. Guide electrodes with a slight declination (10-20° inclined in direction of travel). Weld with a short arc. To improve degassing of the deposit, adopt a low welding speed. Material up to 5 mm can be welded without preheating, when using the adopted electrode diameter. Heavier sections have to be preheated up to about 500°C.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.