

## Classifications

EN ISO 18275-A	AWS A5.5 / SFA-5.5	AWS A5.5M
E 62 4 Mn1NiMo B 4 2 H5	E10018-D2 H4	E6918-D2 H4

## Characteristics and typical fields of application

Basic coated MnNiMo alloyed electrode.

Very low H<sub>2</sub>-content < 5 ml/100 g; extremely high resistance to cracking and high toughness at temperatures as low as -40°C.

For creep resistant steels and cast steel grades, valves and oil tools according to sour gas specification; postweld heat treatment: stress relieving according to parent metal.

## Base materials

G30CrMoV6-4, GS-30CrMoV6-4

Steels acc. ASTM A 487-4Q; AISI 4130

## Typical analysis

	C	Si	Mn	Ni	Mo
wt.-%	0.09	0.3	1.9	0.9	0.4


## Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength	Tensile strength	Elongation A	Impact energy ISO-V KV J		
	R <sub>p0.2</sub>	R <sub>m</sub>	(L <sub>0</sub> =5d <sub>0</sub> )	20°C	-40°C	-50°C
	MPa	MPa	%			
u	650 (≥ 620)	770 (690 - 890)	20 (≥ 18)	120	70 (≥ 47)	60
s	630	730	21	130	70	60

u untreated, as welded

s stress released at 635°C/4h

## Operating data

	Polarity	DC+	Dimension mm	Current A	
	Electrode identification	FOX NiMo / E 62 4 Mn1NiMo B / E10018-D2		2.5 × 350	70 – 100
				3.2 × 350	100 – 150
				4.0 × 450	140 – 200
				5.0 × 450	180 – 250

Choose preheating, interpass temperature and post weld heat treatment (PWHT) as required by the base material.

## Approvals

-