



FCO 307

*Maintenance and repair
Stainless steel open arc wire*

Classification

AWS A5.22 : ~E307T0-3

ISO 17633-A : T 18 8 Mn U NO 3

Description & Applications

Flux cored wire in stainless steel without gas use for welding austenitic stainless steels and manganese steels considered difficult to weld or misidentified. Could be used as buffer layer before hardfacing. Good resistance against cavitation, shocks and corrosion

Main applications: Civil engineering, road, rail and fluvial, quarry, cement. Ideal as buffer layer before hardfacing of grades sensitive to cracking or in case of dissimilar joints between stainless steel and steel construction.

Typical Chemical Composition (%)

C	Si	Mn	Cr	Ni	P	S	Fe
0.10	0.50	6.00	19.0	9.0	0.015	0.008	Rem.

All Weld Metal Mechanical Properties

R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness (3 rd layer)	
400	650	32	180 HB as welded	47 HRC work hardened

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters			Shielding Gas
		Current (A)	Voltage (V)	Stick out (mm)	
FCAW = +	1.2	100 - 300	21 - 35	12 - 25	-
	1.6	150 - 300	24 - 35	15 - 25	

FT En-CN28-16021115/00



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr