



# FCT 309L

*TIG cored wire  
For root pass on dissimilar joint*

## Classification

AWS A5.22 : R309LT1-5

## Description & Applications

Flux cored wire for TIG welding for 309L stainless steel and dissimilar joint (steel with stainless steel). This product is dedicated to the root pass. Indeed this slag protects the reverse side from the oxidation by the atmosphere. Used for application with service temperature between -196°C and +400°C.

**Main applications:** Root pass for steel piping, petro chemical

### Base materials:

UNS	Grade	EN 10088	N° Mat.
S30900	309	X15CrNiSi20-12	1.4828
S30453	304LN	X2CrNiN18-10	1.4311
S30908	309S	X12CrNi23-13	1.4833

## Typical Chemical Composition ( % )

C	Si	Mn	Cr	Ni	Mo	Cu	P	S	Fe
0.03	0.80	1.5	24.5	13.0	0.10	0.10	0.02	0.008	Rem.

## All Weld Metal Mechanical Properties

$R_{p0.2}$ (MPa)	$R_m$ (MPa)	$A_5$ ( % )	KV ( J )	
460	580	35	+20°C	70

## Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters		Shielding Gas
		Current (A)	Voltage (V)	
TIG = +	2.2	80 - 140	-	ISO 14175: I1 (Ar) 6 - 12 L/min

FT En-CN31-160211



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

[www.fsh-welding.com](http://www.fsh-welding.com) - [info@fsh-welding.fr](mailto:info@fsh-welding.fr)