



# FCT 316L

TIG cored wire  
For root pass on 316L

## Classification

AWS A5.22 : R316LT1-5

## Description & Applications

Flux cored wire for TIG welding for 316L stainless steel. This product is dedicated to the root pass. Indeed this slag protects the reverse side from the oxidation by the atmosphere. Used for application with service temperature between -196°C and +350°C.

**Main applications:** Root pass for steel piping, petro chemical

### Base materials:

UNS	Grade	EN 10088	N° Mat.
S31600	316	X5CrNiMo17-12-2	1.4401
S31603	316L	X2CrNiMo17-12-2	1.4404
S31635	316Ti	X6CrNiMoTi17-12-3	1.4571
S30400	304	X5CrNi18-10	1.4301
S30403	304L	X2CrNi18-10	1.4306

## Typical Chemical Composition ( % )

C	Si	Mn	Cr	Ni	Mo	Cu	P	S	Fe
0.03	0.50	0.90	18.5	12.0	2.8	0.10	0.02	0.008	Rem.


## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )	
510	630	32	+20°C	140
			-196°C	50

## Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters		Shielding Gas
		Current (A)	Voltage (V)	
TIG = +	2.2	80 - 140	-	ISO 14175: I1 (Ar) 6 - 12 L/min

FT En-CN30-160211



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

[www.fsh-welding.com](http://www.fsh-welding.com) - [info@fsh-welding.fr](mailto:info@fsh-welding.fr)