



FCW 20/10NB-DH

Flux Cored Wire

Old reference FCW 347

Classification

AWS A5-22 : E347 T0 - 1/4

MaterialN° : 1.4551

EN ISO 17633-A : T19 9 Nb T M3 / C3

Characteristics

Rutile type flux cored wire to weld with shielding gas protection 18%Cr-8%Ni type stainless steel Niobium / Columbium stabilised, suited to weld Ti or Nb stabilised stainless steels. The weld deposit is resistant to intercrystalline corrosion for service temperatures upto 400°C. Excellent weldability and suitable for use with ceramic backing. Excellent weld metal quality and X-ray soundness.

Applications

For welding Steels that are exposed to working temperatures upto 400°C. As well as for cladding/Weld overlay.

Base Materials

UNS	Alloy	EN	Material N°	UGINE
S 30400	304	X5CrNi18-10	1.4301	UGINOX 18-9 B,D,E
S 30403	304L	X2CrNi19-11	1.4306	UGINOX 18-10 L
S 32100	321	X6crNiTi18-10	1.4541	UGINOX 18-10 T
S 34700	347	X6CrNiNb18-10	1.4550	

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Mo	Cu	Nb	P	S	Fe
0.030	0.60	1.40	19.50	10.50	0.10	0.080	0.50	0.020	0.010	base

All Weld Metal Mechanical Properties (Typical)

Conditions	UTS	YS	% Elg	Impact (KV)		LE
	Rm (MPa)	Rp0.2 (MPa)	A ₅	Temp. °C	J	(mm)
AW	650	450	35	-196	34	0.30

Welding Current & Instructions

Welding Mode	Ø Wire (mm)	Welding Mode			Shielding Gas
		Current (A)	Voltage (V)	Stick-out (mm)	ISO 14175
FCAW = +	1.2	120 - 250	23 - 30	15 - 20	M21 (Ar+10-20 %Co ₂) or CO ₂ 18 - 20 l/min

Welding Positions : 1G/PA ; 2G/PC ; 1F ; 2F/PB

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. Fumes: Consult information on MSDS, available upon request.