



FCW 309L

*High productivity 309L type
Flux cored wire*

Classification

AWS A5.22 : E309LT0-1/-4

ISO 17633-A : T 23 12 L R M21(C1) 3

Description & Applications

Flux cored wire for gas shielded (Ar + CO₂) arc welding for 309L stainless steel and for dissimilar joining type 304 or 316 on low alloys steels. The high ferrite content allows an important dilution without cracks. Flux cored wire with high productivity in down hand and fillet welding. Easy slag removal.

Main applications: Pressure vessels, maintenance and repair. Buttering before Low carbon cladding or Final hardfacing

Typical Chemical Composition (%)


C	Si	Mn	Cr	Ni	Mo	Cu	P	S	Fe
0.03	0.70	1.4	23.5	13.0	0.10	0.10	0.02	0.008	Rem.

All Weld Metal Mechanical Properties

R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
460	580	32	-60°C 40

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters			Shielding Gas
		Current (A)	Voltage (V)	Stick out (mm)	
FCAW = +	1.2	100 - 280	23 - 33	10 - 25	ISO 14175 : M21 (Ar/CO ₂) 12 - 20 l/min
	1.6	150 - 400	23 - 35	10 - 25	



FT En-CN09-160211

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr