



# FCW FENI

*Rutile flux cored wire for cast iron*

## Classification

ISO 1071 : T C NiFe-2

## Description & Applications

Rutile flux cored wire for gas shielded (Ar + CO<sub>2</sub>) arc welding of grey, malleable, nodular cast irons. Iron/Nickel weld deposit. Also used for dissimilar weldments between cast irons and steels.

### Base material:

Lamellar cast iron	DIN 1691	GGG-40 à GGG-60
Malleable cast iron	DIN 1692	GTS 35 - GTS 65, GTW 35 – GTW 65
Nodular cast iron	DIN 1693	GGG40 – GGG70

## Typical Chemical Composition ( % )

C	Si	Mn	Ni	P	S	Fe
0.75	0.60	4.0	45.0	<0.015	<0.015	Rem.

## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	Hardness
340	550	16	165 HB

## Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters			Shielding Gas
		Current (A)	Voltage (V)	Stick out (mm)	
FCAW = +	1.2	180 - 280	20 - 28	12 - 25	ISO 14175 : M21 (Ar/CO <sub>2</sub> ) 10 - 20 l/min
	1.6	180 - 350	22 - 28	12 - 25	

FT En-CI06-160211



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.