



FCW M75Cu

*Metal cored wire
Type CORTEN*

Classification

AWS A5.28 : E70C-G H4

ISO 17632-A

T 46 2 Z M M 1 H5

Description & Applications

Metal cored wire with Chromium, Nickel and Copper alloyed for welding COR-TEN type steels with Ar + CO₂ gas shielded. Good weldability, low spatter.

Main applications: Public works, steels construction, shipyard...

Base material:

Steels with improved resistance to atmospheric corrosion

EN- Designation	S235J0W, S235J2W, S355J2G1W COR-TEN A, COR-TEN B, Patinax 37...
-----------------	--

Typical Chemical Composition (%)

C	Si	Mn	Cr	Ni	Cu	P	S	Fe
0.05	0.50	1.10	0.50	0.40	0.40	0.015	0.015	Rem.

Typical All Weld Metal Mechanical Properties

R _e (MPa)	R _m (MPa)	A ₅ (%)	KV (J)	
510	570	24	-20°C	80

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters			Shielding Gas
		Current (A)	Voltage (V)	Stick-out (mm)	
FCAW = +	1.2	100 - 350	15 - 35	12 - 25	ISO 14175 : M21 (Ar/CO ₂) 12 - 15 l/min
	1.6	130 - 450	15 - 35	15 - 25	

FT En-CF08-160211



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr