



# FCW NI625

*Rutile-basic cored wire  
Alloy 625 type*

## Classification

AWS A5.34 : ENiCrMo3T0-4

ISO 12153 : T Ni 6625 (NiCr22Mo9Nb)

## Description & Applications

Flux cored nickel base wire for gas shielded (Ar + CO<sub>2</sub>) arc welding in flat position of high nickel alloys such as Inconel 625\* type as well as for special austenitic stainless steels. Excellent resistance to pitting, crevice and stress corrosion cracking in the presence of chlorides. Could be used for cryogenic applications due to its high mechanical properties at low temperature. Used for dissimilar assembly as low alloy steel and stainless steels or nickel base alloys.

\*Trademarks of INCO ALLOYS

**Main applications:** Cladding on steels of 5% and 9% Ni. Used in the construction of equipment submitted to oxidizing and corrosive attacks at high temperatures.

## Typical Chemical Composition ( % )

C	Si	Mn	Cr	Mo	Fe	Nb	Cu	Ti	P	S	Ni
0.025	0.30	0.40	21.0	9.0	0.40	3.4	0.01	0.15	0.01	0.01	Base

## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
500	780	40	-196°C 70

## Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters			Shielding Gas
		Current (A)	Voltage (V)	Stick-out (mm)	
FCAW = +	1.2	130 - 250	24 - 32	12 - 25	ISO 14175 : M21 (Ar/CO <sub>2</sub> ) 10 - 20 l/min
	1.6	150 - 300	24 - 32	12 - 25	

FT-En-CI03-160211



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

[www.fsh-welding.com](http://www.fsh-welding.com) - [info@fsh-welding.fr](mailto:info@fsh-welding.fr)