



Selectarc Inox 13/4

*Stainless Electrode
With 13% Cr & 4% Ni*

Classification

AWS A 5.4 : E410NiMo-15 EN 1600 : E 13 4 B 4 2
ISO 3581-A : E 13 4 B 4 2

Description & Applications

Basic coated electrode for repair and construction welding of martensitic CrNi steels of similar composition. These steels / castings are used for hydraulic turbines, pumps, valve bodies, compressor parts...Stable arc, easy slag removal, regular weld beads.

Base materials

Martensitic stainless steels and castings:

UNS	Alloy	EN/ Symbol	Material N°
J91540	CA6-NM	G-X5CrNi13-4	1.4313
S41500		X3CrNiMo13-4	1.4313
		G-X4CrNi13-4	1.4317
		G-X5CrNiMo13-4	1.4407
		X3CrNiMo13-4	1.4413
		G-X4CrNiMo13-4	1.4414

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Mo	Fe
0.04	0.3	0.6	12.0	4.2	0.5	Rem.

All Weld Metal Mechanical Properties

$R_{p0,2}$ (MPa)	R_m (MPa)	A_5 (%)	KV (J)
>630	>830	>15	+20°C >50



After PWHT 580°C/8h

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x450
Current	(A)	90	130	150

Redrying 2h at 300°C. Guide electrodes with a slight declination, weld with a short arc. Preheat base material to 100-150°C and keep this temperature during welding. Cool down to room temperature and perform the PWHT.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.