



Selectarc Inox 385

*Stainless Electrode
Highly corrosion resistant*

Classification

AWS A5.4 : E385-16 EN 1600 : E 20 25 5 Cu N L R 1 2
ISO 3581-A : E 20 25 5 Cu N L R 1 2

Description & Applications

Rutile-basic coated electrode for welding fully austenitic highly corrosion resistant stainless steels as 904L, B6 . Good weldability in all positions, except vertical down, stable arc, good slag removal, regular finely rippled weld beads. Due to its alloy composition, high Mo-content and Cu, the weld metal is suited against attacks by phosphoric- and sulphuric acids, it shows a high resistance against pitting and stress corrosion in chloride containing media. It is used at operation temperatures up to 400°C.

Main applications: Pulp and paper industry, transport containers, installations of the chemical industry.

Base materials

UNS	Alloy	EN	Material N°	CLI
S31703	317 L	X2CrNiMo18-15-4	1.4438	
	317 LNM	X2CrNiMoN17-13-5	1.4439	
		G-X7NiCrMoCuNb 25-20	1.4500	
		X5CrNiMoCuTi 20-18	1.4506	
N08904	904L	X1NiCrMoCu25-20-5	1.4539	URB6(N)

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Mo	Cu	Fe
<0.03	0.8	1.4	20.5	25.0	4.5	1.5	Rem.

All Weld Metal Mechanical Properties

R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>370	>570	>35	+20°C >70

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x350
Current	(A)	50-70	70-100	90-130

Redrying 2-3h at 250-300°C. Guide electrodes with a slight declination, weld with a short arc and prevent a high heat input by applying the stringer bead technique (weaving max. 2 times core wire diameter). Interpass temperature : < 150°C.

ind.12



= + ~ 70V



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.