



MIG 20/10MS

Old reference: MIG 316LSi

Classification

ISO 14343-A : G 19 12 3 L Si
 AWS A5.9 : ER316LSi

Material N° : 1.4430

Description & Applications

Low carbon solid wire for joining of stabilised stainless steels (316, 316L...) stabilised or not. Service temperature from -120°C up to +400°C.

Main applications: Chemical and petrochemical industries, refineries, food industries...

Typical Chemical Composition (%)

C	Si	Mn	Cr	Ni	Mo	Cu	P	S	Fe
0.018	0.85	1.7	18.5	12.2	2.7	0.1	<0.02	<0.01	Rem.

All Weld Metal Mechanical Properties

R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)	
430	620	35	+20°C	120
			-196°C	45

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters		Shielding Gas
		Pulsed arc (A)	(V)	
MIG = +	0.8	100-150	22-27	Ar + 2%CO ₂ Ar + 1%O ₂ 18-20 l/min
	1.0	120-200	24-28	
	1.2	140-220	24-28	
	1.6	180-260	24-30	

Ind.10



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.