



MIG FENI60

Classification

ISO 1071 : S C NiFe-2

Description & Applications

Solid wire for GMAW and reparation of ferritic or martensitic spheroidal cast iron. Could be also used for heterogeneous assembly of nodular cast iron with steel or copper alloy or nickel alloy. Weld deposit characterized by good resistance against cracking and easily machinable.

Main applications: Cast iron pipe, flanges...

Typical Chemical Composition (%)

	C	Si	Mn	Ni	Cu	Al	Ti	P	S	Fe
Min			1.0	45						
Max	2.0	4.0	5.0	60	2.5	1.0	-	0.03	0.03	Rem.
Type	0.10	0.30	3.6	54.2	1.8	0.02	0.30	0.005	0.010	Rem.

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
Min	-	-	-	-
Max	-	-	-	-
Type	300	500	25	As welded ~200HB

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters		Shielding Gas
		Current (A)	Voltage (V)	
GMAW = +	0.8	70 - 180	18 - 26	ISO 14175: I1 (100% Ar) I3 (Ar+10-30%He) Z (Ar+He+H+CO ₂) 15-20 l/min
	1.0	80 - 220	18 - 28	
	1.2	150 - 320	22 - 32	
	1.6	220 - 380	24 - 34	

Preheating of massive cast iron parts: 150-200°C. interpass temperature: <120°C. Reduce the heat input to a minimum (low welding energy) to avoid cracks in base material.

FT En-MI22-170116

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr