

Specifications:

Alloy	Working Temperature (°C)	DIN EN ISO 17672	AWS A-5.8	DIN 8513	EN ISO 3677	AMS
Al-Si	590	Al 112	BAISi-4	L-Al Si 12	B- Al88Si-575-585	-

Characteristics:

TBM 12NCs 20 Composite rod consisting of a homogeneous mixture of aluminium alloy and a non-corrosive flux for high-strength brazing of sheet, forged or cast parts in aluminium alloys. non-corrosive flux. Alloy to Flux ratio is maintain at 86:14. This wire is adaptable for brazing of Aluminium and Low Aluminium alloys with solidus temperature $\geq 630^{\circ}\text{C}$. Alloy used with torch, Induction and furnace brazing heat source. High Fluid filler alloy with non-corrosive flux gives very good capillary action, No extra flux required. The higher %Cs containing flux is more aggressive than conventional non-corrosive flux. The ductility and penetration of the alloy with excellent corrosion resistance. No post-braze cleaning required being non-corrosive flux. Excellent electrical conductivity Good colour match on aluminium. No separate flux to apply, need flux handling systems or corrosive flux to apply. Product does not fume.

Applications:

TBM 12 NCs 20 Aluminium parts repair, Aluminium connectors, heat exchanger, air conditioning and refrigeration systems, connection of pipe Aluminium, radiators, automotive etc. **Strongly recommended for Magnesium bearing aluminium-alloy (Mg<1.20%)**. Also used for joining Copper to Aluminium alloy.

Typical Chemical Compositions (%):

Al	Si	Zn	Fe	Mn	Mg	Cd	Pb	Max. impurities
Rem.	12.00	<0.20	<0.80	<0.15	<0.10	<0.01	<0.025	<0.15





Typical Physical Properties:

Colour	Solidus (°C)	Liquidus (°C)	Density g/cm ³	Elongation %	Tensile strength (MPa)	Electrical Conductivity (%IACS)	Electrical Resistivity (Micro-ohm-cm)
Metallic aluminium	575	585	2.65	20	140	-	-

Properties of Brazed Joint:

The properties of a brazed joint dependent upon numerous factors including base metal properties, joint design, metallurgical interactions between the base metal and the filler metal.

Standard size and Types:

Size (mm)	Type			 OXYACETYLENE	 INDUCTION	 AÉRO-PROPANE	 FOUR/OVEN
	Cut Length	Coil	Preforms				
1.20 - 3.00	√	√	√	√	√	√	√

Customised sizes other than above standard dimensions are solicited case to case basis

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.