



# TIG 20/10MNBS

Old reference: TIG 318Si

## Classification

ISO 14343-A : W 19 12 3 Nb Si  
 AWS A5.9 : ER318 type

Material N° : 1.4576

## Description & Applications

Low carbon solid rod for TIG welding of stabilised stainless steels (318, 316Ti...). Good intergranular resistant corrosion. Service temperature from -120°C up to +400°C. The TIG process is particularly suited for welding of piping systems, works of fine thinness equal or inferior than 3 mm and for penetration passes.

**Main applications:** Applied in the petrochemical industries and for sea water applications...

## Typical Chemical Composition ( % )

C	Si	Mn	Cr	Ni	Mo	Nb	Cu	P	S	Fe
0.04	0.85	1.7	19.6	11.5	2.6	0.6	0.2	<0.02	<0.01	Rem.

## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
400	620	35	+20°C 120

## Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	Ar : 6-12 l/min Back shielding : Argon / Nitrogen : 3-6 l/min

ind.11



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.