



TIG HB48HT

Classification

EN 14700 : S Fe8

Material N° : ~1.2367

Description & Applications

Solid rod for TIG hardfacing of steels with similar chemical composition. The weld deposit distinguishes itself by its toughness and heat resistance. Therefore this grade is used for overlay and builds up of machinery parts and tools subject to impact, compression and wear used at operating temperatures up to 550°C.

Main applications: For forging and drawing dies, for building up hammers, dies, swages, hot shear blades, rollers, cast moulds.

Base materials:

High strength carbon steels and hot working steels:

Material N°	DIN classification	Material N°	DIN classification
1.2311	40CrMnMo 7	1.2367	X38CrMoV 5 3
1.2343	X38CrMoV 5 1	1.2606	X37CrMoW 5 1
1.2344	X40CrMoV 5 1	1.2713	55NiCrMoV 6
1.2365	X32CrMoV 3 3	1.2714	56NiCrMoV 7

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Mo	W	Nb	V	Ti	P	S	Fe
Min	0.2			5								
Max	2		3	20	5	2	10	2				Rem.
Type	0.25	0.30	0.60	5.1	3.6	0.001	0.001	0.001	0.60	0.020	0.010	Rem.

All Weld Metal Mechanical Properties

Hardness (as welded)
42-47 HRC

Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	ISO 14175 : I1 (Ar) 6-12 L/min

Preheat the workpiece to 250-400°C depending on thickness and alloy composition. Keep low temperature during welding and let the workpiece cool slowly.

Subsequent machining is possible by gridding or with tungsten carbide tool.

FT En-TR09-170719

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr