



TIG HBC62

Classification

DIN 8555 : WSG 4-GZ-60-S
EN 14700 : S Fe4

Material N° : 1.3348

Description & Applications

Solid rod for TIG welding to surfacing. Composition of high speed steel, used for hardsurfacing cold working tools as lathe tools, drilling tools, cutting tools.

Main applications: Hardfacing and repairing of high speed steels like 85WMoCrV6.5.4.2, 1.3339, 1.3333 and others.

Typical Chemical Composition (%)

C	Si	Mn	Cr	Mo	V	W	Fe
1.0	0.4	0.2	3.6	8.5	1.8	1.6	Rem.

All Weld Metal Mechanical Properties

Hardness
~62 HRC

Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	Ar : 6-12 l/min

Tool steels have to be preheated to 350-450°C, depending on the thickness and composition.

ind.10



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.