

**Classifications**

<b>EN ISO 14343-A</b>	<b>AWS A5.9 / SFA-5.9</b>
W 19 12 3 L Si	ER316LSi

**Characteristics and typical fields of application**

TIG rod of W 19 12 3 L Si / ER316LSi type for welding austenitic stainless steel of 17Cr-12Ni-2.5Mo type or similar. Also suitable for welding steels that are stabilized with titanium or niobium, such as 1.4571 / 316Ti for service temperatures not exceeding 400°C. For higher temperatures a niobium-stabilized consumable such as Böhler SAS 4-IG (Si) is required. Excellent resistance to general, pitting and intercrystalline corrosion in chloride containing environments. Intended for severe service conditions, e.g. in dilute hot acids. Microstructure is austenite with 5 – 10% ferrite. Max. service temperature 400°C.

**Base materials**

1.4401 X5CrNiMo17-12-2, 1.4404 X2CrNiMo17-12-2, 1.4409 GX2CrNiMo19-11-2, 1.4429 X2CrNiMo17-12-3, 1.4432 X2CrNiMo17-12-3, 1.4435 X2CrNiMo18-14-3, 1.4436 X3CrNiMo17-12-3, 1.4571 X6CrNiMoTi17-12-2  
UNS S31600, S31603, S31635, S31640, S31653  
AISI 316L, 316Ti, 316Cb


**Typical analysis**

	C	Si	Mn	Cr	Ni	Mo	Ferrit
wt.-%	0.02	0.9	1.7	18.5	12.0	2.6	7 FN (WRC-92)

**Mechanical properties of all-weld metal - typical values (min. values)**

Condition	Yield strength	Tensile strength	Elongation A	Impact energy ISO-V KV J		Hardness
	R <sub>p0.2</sub>	R <sub>m</sub>	(L <sub>0</sub> =5d <sub>0</sub> )	20°C	-196°C	
u	MPa 470 (≥ 320)	MPa 610 (≥ 510)	% 31 (≥ 25)	140	(≥ 32)	210

**Operating data**

	<b>Polarity</b>	DC-	<b>Dimension mm</b>
	<b>Shielding gas (EN ISO 14175)</b>	I1 R1 ≤ 5% H <sub>2</sub>	0.8
	<b>Rod marking</b>	+ W 19 12 3 LSi / ER 316 LSi	1.0
			1.2
			1.6 × 1000
			2.0 × 1000
			2.4 × 1000
		3.2 × 1000	

Heat input max. 2.0 kJ/mm, interpass temperature max. 150°C.

Post-weld heat treatment generally not needed. In special cases, solution annealing can be performed at 1050°C followed by water quenching.

Shielding gas: Ar, Ar + 20 – 30% He, Ar + 1 – 5% H<sub>2</sub>

**Approvals**

TÜV (00488), DB (43.132.35), DNV, CE