

## Classifications

EN ISO 17632-A	EN ISO 17632-B	AWS A5.29 / SFA-5.29
T 50 6 1Ni P M21 1 H5	T 55 6 T1-1M21A-N2-UH5	E81T1-Ni1M-JH4

## Characteristics and typical fields of application

Seamless rutile, Nickel alloyed, flux cored wire for single- or multilayer welding of Carbon, Carbon-Manganese steels and high strength steels with Argon-CO<sub>2</sub>. Main features: excellent weldability in all positions, excellent bead appearance, very low spatter losses, fast freezing and easy to remove slag. The exceptional mechanical properties of this wire even at low temperatures (-60°C), also after post weld heat treatment make it especially suitable for offshore applications. The wire is CTOD tested at -10°C. (14°F) This product can be used in sour gas applications. (HIC tested acc. to NACE TM-0284). Test values for SSC are available upon request.

## Base materials

S355JR, S355JO, S355J2, S450JO, S355N-S460N, S355NL-S460NL, S355M-S460M, S355ML-S460ML, S460Q, S500Q, S460QL, S500QL, S460QL1, S500QL1, P355GH, P355NH, P420NH, P460NH, P355N-P460N, P355NH-P460NH, P355NL1-P460NL1, P355NL2-P460NL2, L245NB-L415NB, L245MB-L485MB, L360QB-L485QB, aldur 500Q, aldur 500QL, aldur 500QL1  
 ASTM A 350 Gr. LF2; A 516 Gr. 65, 70; A 572 Gr. 42, 50, 60, 65; A 573 Gr. 70; A 588 Gr. B, C, K; A 633 Gr. A, C, D, E; A 662 Gr. B, C; A 678 Gr. B; A 707 Gr. L2, L3; A 841 Gr. A, B, C; API 5 L X42, X52, X60, X65, X70, X52Q, X60Q, X65Q, X70Q

## Typical analysis

	Gas	C	Si	Mn	Ni
wt.-%	M21	0.05	0.45	1.3	0.85

## Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength R <sub>e</sub>	Tensile strength R <sub>m</sub>	Elongation A (L <sub>0</sub> =5d <sub>0</sub> )	Impact energy ISO-V KV J	
	MPa	MPa	%	-40°C	-60°C
u	550 (≥ 500)	610 (560–690)	25 (≥ 19)	100	75 (≥ 47)
s	520 (≥ 500)	580 (560–690)	29 (≥ 19)	60	

u untreated, as welded – shielding gas M21

s stress relieved 550 -600°C / 2h – shielding gas M21

## Operating data

	Polarity	DC+	Dimension mm
	Shielding gas (EN ISO 14175)	M21, M33	1.0
			1.2
			1.4
			1.6

Welding with standard GMAW-facilities possible

## Approvals

TÜV (06226), DB (42.052.11), DNV, ABS, LR, BV, RINA, RS, CWB, CE